

%50 EKOPE PCR F



The test results of the film produced using 50% EKOPE PCR F are shared in the table as an example. It has no binding force.

TEST		METHOD	UNIT	RESULTS
Tensile Strength at Break	MD	ASTM D882	Mpa	24-30
	TD			22-28
Elongation at Break	MD	ASTM D882	%	650-750
	TD			750-850

***Thickness is 50 micron. B.U.R 1.749 Die gap:1.5 mm**