

%50 EKOPE PCR S



The test results of the film produced using 50% EKOPE PCR S are shared in the table as an example. It has no binding force.

TEST		METHOD	UNIT	RESULTS
Tensile Strength at Break	MD	ASTM D882	Mpa	20-24
	TD			17-22
Elongation at Break	MD	ASTM D882	%	500-600
	TD			650-750

***Thickness is 50 micron. B.U.R 1.749 Die gap:1.5 mm**